

# CL-750 N

## Promoted Chloride Adsorbent

BASF CL-750 N is a spherical surface modified adsorbent, custom formulated to provide optimum adsorption of HCl from vapor phase process streams.

### Description

BASF CL-750 N is particularly appropriate for use in vapor phase chloride traps in catalytic reforming processes where optimum HCl adsorption capacity and minimization of polymer formation is desirable.

### Applications

BASF CL-750 N is particularly appropriate for use in vapor phase chloride traps in catalytic reforming processes where optimum HCl adsorption capacity and minimization of polymer formation is desirable. BASF CL-750 N is an excellent HCl scavenger for these streams at both ambient and elevated temperatures. The use of BASF CL-750 N chloride adsorbent allows continuous operation without the problems associated with water washing of chloride deposits in process equipment.

With its superior adsorption capacity and high porosity, CL-750 N is appropriate for the removal of HCl from a variety of vapor phase streams in numerous petrochemical production processes.

### Safety & handling

BASF CL-750 N is classified as non dangerous and does not produce significant toxic effect with reasonable exposure. Normal good housekeeping and operating procedures should ensure personnel safety. The data contained herein are for general informational purpose only. Please refer to the material safety data sheet for specific, complete information regarding the product.

### Available Packaging

- 1200 kg super sacks

### Chemical composition (wt %), typical

<b>Al<sub>2</sub>O<sub>3</sub> + surface modifier (inorganic, non-toxic)</b>	95.5
--	------

<b>SiO<sub>2</sub></b>	0.015
------------------------	-------

<b>LOI (1000°C)</b>	5
---------------------	---

\* These indicative properties do neither represent process capabilities nor specifications.

### Physical properties, typical

<b>Pore Volume, ml/g</b>	0.5
--------------------------	-----

<b>Loose bulk density, kg/m<sup>3</sup></b>	760
---	-----

<b>Surface area, m<sup>2</sup>/g</b>	150
--------------------------------------	-----

<b>Crush Strength (5 mesh eq), kg</b>	14
---------------------------------------	----

<b>Sizes</b>	1/8" (3.2 mm)
--------------	---------------

\* These indicative properties do neither represent process capabilities nor specifications.

## About Us

BASF's Catalysts division is the world's leading supplier of environmental and process catalysts. The group offers exceptional expertise in the development of technologies that protect the air we breathe, produce the fuels that power our world and ensure efficient production of a wide variety of chemicals, plastics and other products, including advanced battery materials. By leveraging our industry-leading R&D platforms, passion for innovation and deep knowledge of precious and base metals, BASF's Catalysts division develops unique, proprietary solutions that drive customer success.

**BASF - We create chemistry**

### Americas

BASF Corporation  
25 Middlesex/Essex Turnpike  
Iselin, New Jersey, 08830, USA  
Tel : +1-732-205-5000  
Fax: +1-732-205-7725  
Email: [catalysts-america@basf.com](mailto:catalysts-america@basf.com)

### Asia Pacific

BASF (China) Company Limited  
300 Jiang Xin Sha Road,  
Pudong, Shanghai 200137  
P.R. China  
Tel: +86-21-2039 2549  
Fax: +86-21-2039 4800-2549  
Email: [catalysts-asia@basf.com](mailto:catalysts-asia@basf.com)

### Europe, Middle East, Africa

BASF De Meern BV Catalysts  
The Netherlands  
Tel: +31-30-666 9437  
Email: [catalysts-europe@basf.com](mailto:catalysts-europe@basf.com)

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required. © 2015 BASF