

Sulfuric Acid Catalyst

O4-115 SS11x4 / SR10x5 / Quattro

Application

For the catalytic oxidation of SO₂ in the production of sulfuric acid. Because of its excellent low temperature activity, catalyst O4-115 may be installed as an ignition layer or full bed application.

Composition

Vanadium oxides, alkali sulphates and cesium promoted on a special carrier.

Form

- Star Rings of 11x4 mm ODxD (SS11x4)
- Extrudate Rings of 10x5 mm ODxD (SR10x5)
- Quattro of 13x3.2mm ODxD

Ignition temperature (theoretical)

min. 340°C (min. 644°F)

(depending on gas composition)

Operating temperature

SS and SR shape:

380-630°C (716-1165°F)

(depending on gas composition)

Quattro shape:

380-630°C (716-1165°F)

(depending on gas composition)

Thermal stability

Stable at continuous operation up to 630°C (1165°F).

Packaging

Non-returnable containers

- 200 l corrugated steel drum
- 1000 l bulk bag

Bulk Density	SS11x4	SR10x5	Quattro
approx. kg/l	0.5	0.50	0.5
approx. lb/l	1.10	1.10	1.10

Knife Edge Hardness	SS11x4	SR10x5	Quattro
approx. kg	7.0	7.0	10.0
approx. lb	15.0	15.0	22.1

Safety Data Sheets (SDS)

A safety data sheet covering the necessary information is available on request.

Storage

Catalyst should be stored in its original container in a covered and dry area, protected from access by humidity and moisture.

Note

The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

About Us

BASF's Catalysts division is the world's leading supplier of environmental and process catalysts. The group offers exceptional expertise in the development of technologies that protect the air we breathe, produce the fuels that power our world and ensure efficient production of a wide variety of chemicals, plastics and other products, including advanced battery materials. By leveraging our industry-leading R&D platforms, passion for innovation and deep knowledge of precious and base metals, BASF's Catalysts division develops unique, proprietary solutions that drive customer success.

BASF - We create chemistry

Americas

BASF Corporation
25 Middlesex/Essex Turnpike
Iselin, New Jersey, 08830, USA
Tel : +1-732-205-5000
Email: catalysts-america@basf.com

Asia Pacific

BASF (China) Company Limited
300 Jiang Xin Sha Road,
Pudong, Shanghai 200137
P.R. China
Tel: +86-21-2039 2549
Email: catalysts-asia@basf.com

Europe, Middle East, Africa

BASF Services Europe GmbH
Rotherstraße 11
10245 Berlin, Germany
Tel: +49-30-20055000
Email: catalysts-europe@basf.com

www.catalysts.basf.com/sulfuric-acid

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required. © 2015 BASF

BASF- 9588 08/22