

# Sorbead® Air WS

**Sorbead® Air WS is an alumino-silicate gel in our line of highly efficient adsorbents ideally suited for compressed air drying.**

## Product description

Sorbead® Air WS is a high-performance adsorbent designed for applications in compressed air industry. It is available as hard, spherical beads. These beads are adsorbents for water, and resist crushing and attrition. The product has an above average drying capacity, low required desorption temperature, long life span, and high mechanical strength. When used to dry compressed air, these properties effectively reduce operating costs in manufacturing plants.

## Applications

Sorbead® Air WS is used for drying of compressed air. It is the only 100% water-resistant adsorbent with a high adsorption capacity, and is most frequently used as a protective layer in combination with Sorbead® Air R. Sorbead® Air WS is ideal for applications where adsorbent regeneration with humid gas occurs.

## Safety & handling

Sorbead® Air WS is classified as nontoxic and does not produce toxic effects upon reasonable exposure. It is also known to have high thermal stability and hydrothermal stability. Normal housekeeping and operating procedures should ensure personnel safety. The data contained herein are for general

informational purpose only. Please refer to the Safety Data Sheet for specific, complete information regarding these products.

## Physical Properties

Chemical Composition	97 % SiO <sub>2</sub> , 3 % Al <sub>2</sub> O <sub>3</sub>
Surface Area, m <sup>2</sup> /g	630-650
Pore volume, ml/g	0.43-0.45
Bulk Density, kg/L	0.7
Equilibrium capacity for water vapor at 25 °C and relative humidity 80%	34.0-36.0
Crush Strength, N	90-100
Attrition, wt %	0.05-0.1
Grain size (mm)	2-5
Water (liquid) resistant	Yes
Typical desorption temperature (°C)	120-150
Pressure dew point of surrounding air can get down to (°C)	-60

## Typical distribution of grain size

- 2.0-5.0 mm
- Other sizes on request

## Packaging

- Big bag, 1,653 lb, 750 kg
- Steel drums, 287 lb, 130 kg
- Poly bag, 55 lb, 25 kg

## About Us

BASF's Catalysts division is the world's leading supplier of environmental and process catalysts. The group offers exceptional expertise in the development of technologies that protect the air we breathe, produce the fuels that power our world and ensure efficient production of a wide variety of chemicals, plastics and other products, including advanced battery materials. By leveraging our industry-leading R&D platforms, passion for innovation and deep knowledge of precious and base metals, BASF's Catalysts division develops unique, proprietary solutions that drive customer success.

**BASF - We create chemistry**

### Americas

BASF Corporation  
25 Middlesex/Essex Turnpike  
Iselin, New Jersey, 08830, USA  
Tel : +1-732-205-5000  
Fax: +1-732-205-7725  
Email: [catalysts-america@basf.com](mailto:catalysts-america@basf.com)

### Asia Pacific

BASF (China) Company Limited  
300 Jiang Xin Sha Road,  
Pudong, Shanghai 200137  
P.R. China  
Tel: +86-21-2039 2549  
Fax: +86-21-2039 4800-2549  
Email: [catalysts-asia@basf.com](mailto:catalysts-asia@basf.com)

### Europe, Middle East, Africa

BASF De Meern BV Catalysts  
The Netherlands  
Tel: +31-30-666 9437  
Email: [catalysts-europe@basf.com](mailto:catalysts-europe@basf.com)

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required. © 2015 BASF

[www.catalysts.basf.com/SorbeadAir](http://www.catalysts.basf.com/SorbeadAir)

BASF-10605 Rev. 08/2020